

**Ramset fasteners may be specified by their type or catalog number to satisfy fastening requirements.**

## PIN SPECIFICATIONS

- Made from AISI 1060-1065 steel. Austempered to a core hardness of 52-56 Rc
- Typical tensile strength: 270,000 psi
- Typical shear strength: 162,000 psi
- **STANDARD FINISHES**
  - Proprietary black
  - Mechanical zinc plate to a minimum thickness of .0002 meets requirements of ASTM B695
  - Electroplated zinc with yellow chromate
  - Ramguard

## APPROVALS/LISTINGS

- **ICC Evaluation Service, Inc.**
  - #ESR-2579 TrakFast Pins
  - #ESR-1955 T3 Fasteners
- **City of Los Angeles**
  - #RR-25739 T3 pins
  - #RR-25264 TrakFast pins

## COLLATED GAS FASTENERS IN CONCRETE (TRAKFAST, T2 AND T3)

PART NUMBER SERIES	SHANK DIAMETER (INCH)	MINIMUM PENETRATION (INCH)	INSTALLED IN STONE AGGREGATE CONCRETE CONCRETE COMPRESSIVE STRENGTH ALLOWABLE LOAD - <i>Ultimate Load</i>					
			2000 PSI		3000 PSI		4000 PSI	
			TENSION (LBS)	SHEAR (LBS)	TENSION (LBS)	SHEAR (LBS)	TENSION (LBS)	SHEAR (LBS)
FPP - Straight Shank	0.109	5/8	<b>60</b> <i>434</i>	<b>55</b> <i>546</i>	<b>55</b> <i>453</i>	<b>75</b> <i>615</i>	<b>55</b> <i>472</i>	<b>95</b> <i>685</i>
		3/4	<b>60</b> <i>595</i>	<b>80</b> <i>650</i>	<b>55</b> <i>583</i>	<b>95</b> <i>699</i>	<b>55</b> <i>571</i>	<b>115</b> <i>749</i>
FPP - Step Shank	0.104/0.118	3/4	.....	.....	.....	.....	<b>51</b> <i>256</i>	<b>83</b> <i>418</i>
			2000 PSI		4000 PSI		6000 PSI	
			TENSION (LBS)	SHEAR (LBS)	TENSION (LBS)	SHEAR (LBS)	TENSION (LBS)	SHEAR (LBS)
T3 Straight Shank	0.125	5/8	<b>83</b> <i>414</i>	<b>109</b> <i>611</i>	<b>78</b> <i>426</i>	<b>80</b> <i>574</i>	.....	.....
		3/4	<b>107</b> <i>541</i>	<b>156</b> <i>855</i>	<b>104</b> <i>593</i>	<b>195</b> <i>977</i>	.....	.....
T3 Step Shank	0.104/0.125	5/8	.....	.....	<b>60</b> <i>357</i>	<b>117</b> <i>587</i>	<b>107</b> <i>533</i>	<b>191</b> <i>957</i>

PART NUMBER SERIES	SHANK DIAMETER (INCH)	MINIMUM PENETRATION (INCH)	INSTALLED IN STONE AGGREGATE CONCRETE CONCRETE COMPRESSIVE STRENGTH ALLOWABLE LOAD - <i>Ultimate Load</i>					
			3000 PSI LIGHT WEIGHT CONCRETE		3000 PSI LIGHT WEIGHT CONCRETE WITH METAL DECK		HOLLOW CONCRETE MASONRY UNITS (CMU ANY LOCATION)	
			TENSION (LBS)	SHEAR (LBS)	TENSION (LBS)	SHEAR (LBS)	TENSION (LBS)	SHEAR (LBS)
FPP - Straight Shank	0.109	5/8	<b>35</b> <i>234</i>	<b>55</b> <i>403</i>	<b>30</b> <i>239</i>	<b>205</b> <i>1025</i>	<b>35</b> <i>347</i>	<b>50</b> <i>435</i>
		3/4	<b>80</b> <i>630</i>	<b>100</b> <i>756</i>	<b>40</b> <i>330</i>	<b>235</b> <i>1248</i>	.....	.....
FPP - Step Shank	0.104/0.118	3/4	.....	.....	.....	.....	<b>36</b> <i>184</i>	<b>58</b> <i>290</i>
T3 Straight Shank	0.125	5/8	<b>84</b> <i>418</i>	<b>108</b> <i>540</i>	<b>72</b> <i>361</i>	<b>242</b> <i>1210</i>	<b>20</b> <i>243</i>	<b>34</b> <i>264</i>
		3/4	<b>108</b> <i>540</i>	<b>173</b> <i>864</i>	<b>93</b> <i>470</i>	<b>288</b> <i>1442</i>	.....	.....
T3 Step Shank	0.104/0.125	5/8	.....	.....	<b>54</b> <i>269</i>	<b>230</b> <i>1150</i>	<b>71</b> <i>357</i>	<b>123</b> <i>613</i>

**Note 1:** ALLOWABLE loads are shown in the LARGE BOLD font, *Ultimate* loads are shown in smaller italic font. **Note 2:** Testing conducted in accordance with ICC AC70 & ASTM E1190. **Note 3:** Safety factors are based on coefficient of variation. In accordance with ICC AC70, the safety factor will be no less than 5. **Note 4:** Values shown in concrete are for the fastener only. Connected members must be investigated separately. **Note 5:** Cyclic, fatigue, shock loads, and other design criteria may require a different safety factor. **Note 6:** Job site testing may be required to determine actual job site values. **Note 7:** Minimum edge distance in concrete is 3 inches unless otherwise approved. **Note 8:** For SI: 1 lbf = 4.448 N, 1 inch = 25.4 mm, 1 ksi = 6.89MPa. **Note 9:** T3 straight shank allowable tension value in face shell of hollow CMU is 133 lbs.

**FASTENERS IN CONCRETE**

FASTENER PART NUMBER	SHANK DIA. (INCH)	MINIMUM PENETRATION (INCH)	INSTALLED IN STONE AGGREGATE CONCRETE CONCRETE COMPRESSIVE STRENGTH ALLOWABLE LOAD - <i>Ultimate Load</i>									HOLLOW BLOCK Grade N, Type 1	
			4000 PSI			6000 PSI			3000 PSI Light weight LOWER FLUTE			FACE SHELL Min 1-1/4" face thickness	
			TENSION (LBS)	SHEAR (LBS)	TENSION (LBS)	SHEAR (LBS)	TENSION (LBS)	SHEAR (LBS)	TENSION (LBS)	SHEAR (LBS)	TENSION (LBS)	SHEAR (LBS)	
GAS ASSEMBLIES	MP034TH*, M034* M100*, BR2*	5/8	<b>78</b> 426	<b>80</b> 574	<b>62</b> 308	.....	.....	<b>72</b> 361	<b>242</b> 1210	<b>133</b> 691	.....	.....	
		3/4	<b>104</b> 593	<b>195</b> 977	<b>132</b> 658	<b>206</b> 1057	<b>93</b> 470	<b>288</b> 1442	<b>84</b> 444	<b>84</b> 446			
	14STUD	0.125	5/8	<b>91</b> 454	.....	.....	<b>57</b> 373	.....	.....	.....	.....		
	M034BB	0.104/.118	3/4	<b>51</b> 256	<b>83</b> 418	.....	.....	.....	.....	<b>36</b> 184	<b>58</b> 290		
	34 CLIP	0.104/.125	5/8	<b>62</b> 310	.....	.....	<b>106</b> 528	.....	.....	<b>44</b> 220	.....	.....	
GAS ASSEMBLIES	38HSMP034, 12HSMP034 34HSMP034, 10HSMP034 114HSMP034, 14TRHMP034 38TRHMP034, TSHMP034 12CCMP034L, 34CCMP034L	0.104/.125	5/8	<b>60</b> 357	<b>117</b> 587	<b>107</b> 533	<b>191</b> 957	<b>54</b> 269	<b>230</b> 1150	<b>71</b> 357	<b>123</b> 613		
	POWDER ASSEMBLIES	M100BB, 38HSS10 12HSS10, 34HSS10 10HSS10, 14TRHSS10, 38TRHSS10	0.125/.150	3/4	<b>107</b> 559	<b>213</b> 1067	<b>161</b> 803	<b>248</b> 1240	<b>96</b> 478	<b>231</b> 1156	<b>102</b> 512	<b>166</b> 831	

\* ESR-1955 pin data applies. **Note 1:** ALLOWABLE loads are shown in the **LARGE BOLD** font, *Ultimate* loads are shown in *smaller italic* font. **Note 2:** Testing conducted in accordance with ICC AC70 & ASTM E1190 **Note 3:** Safety factors are based on coefficient of variation. In accordance with ICC AC70, the safety factor will be no less than 5. **Note 4:** Values shown in concrete are for fastener only. Connected members must be investigated separately. **Note 5:** Cyclic, fatigue, shock loads and other design criteria may require a different safety factor. **Note 6:** Job-site testing may be required to determine actual job site values. **Note 7:** Minimum edge distance is 3 inches unless otherwise approved. In hollow block applications, no more than one fastener per cell. **Note 8:** For SI: 1 lbf = 4.448 N, 1 inch = 25.4 mm, 1 ksi = 6.89MPa.

**GAS FASTENERS IN STEEL**

PART NUMBER	SHANK DIAMETER (INCH)	TYPE OF SHANK	INSTALLED IN A36 STRUCTURAL STEEL STEEL THICKNESS INCHES ALLOWABLE LOAD - <i>Ultimate Load</i>					
			3/16 (.1875)		1/4 (.250)		3/8 (.375)	
			TENSION (LBS)	SHEAR (LBS)	TENSION (LBS)	SHEAR (LBS)	TENSION (LBS)	SHEAR (LBS)
FPP012	0.109	SMOOTH	<b>195</b> 1047	<b>292</b> 1570	<b>223</b> 1220	<b>278</b> 1526	<b>181</b> 1048 <sup>7</sup>	<b>186</b> 1076 <sup>7</sup>
M012 FPP012S	0.104/0.118	SMOOTH	.....	.....	<b>148</b> 744	<b>157</b> 787	<b>166</b> 832 <sup>7</sup>	<b>157</b> 787 <sup>7</sup>
T3012	0.125	SMOOTH	<b>63</b> 676	<b>162</b> 1356	<b>239</b> 1285	<b>211</b> 1417	<b>113</b> 914 <sup>8</sup>	<b>197</b> 1327 <sup>8</sup>
T3012S	0.125	TAPER SMOOTH	.....	.....	<b>237</b> 1184	<b>356</b> 1782	<b>189</b> 943 <sup>10</sup>	<b>392</b> 1960 <sup>7</sup>
INSTALLED IN ASTM A 572 GRADE 50 STEEL STEEL THICKNESS INCHES								
T3012	0.125	SMOOTH	<b>103</b> 733	<b>222</b> 1682	<b>147</b> 950	<b>119</b> 973	<b>147</b> 856 <sup>9</sup>	<b>112</b> 1014 <sup>9</sup>

**Note 1:** ALLOWABLE loads are shown in the **LARGE BOLD** font, *Ultimate* loads are shown in *smaller italic* font. **Note 2:** Testing conducted in accordance with ICC AC70 & ASTM E1190. **Note 3:** Safety factors are based on coefficient of variation. In accordance with ICC AC70, the safety factor will be no less than 5. **Note 4:** Cyclic, fatigue, shock loads and other design criteria may require a different safety factor. **Note 5:** Job site testing may be required to determine actual job site values. **Note 6:** Values shown are for fasteners that have the entire pointed end of the fastener driven through the steel plate; except as noted below. **Note 7:** Fastener penetration is .31" minimum. **Note 8:** Fastener penetration is .29" minimum. **Note 9:** Fastener penetration is .27" minimum. **Note 10:** Fastener penetration is .25" minimum. **Note 11:** For SI: 1 lbf = 4.448 N, 1 inch = 25.4 mm, 1 ksi = 6.89MPa